Flat Sheet Ceramic Membrane

Model Code: NPC-F-200

Introduction

Plate-like ceramic sheets in frame modules; filtrate drawn perpendicularly. Flat sheet ceramic membranes are typically outside-in flow.

General Specification	
Model Code	NPC-F-200
Membrane Type	Flat Sheet Ceramic
Total Width	200 *mm*
Channel Width	3 *mm*
Thickness	11 *mm*
Length	1000 *mm*
Filtration Surface Area	~0.422 m^2
Filtration Mode	Dead-end , typically vacuum-driven
Operating Pressure	0.1 – 0.8 bar (typical for submerged MBR or vacuum-driven configurations)
Operating Temperature	5 – 80°C
pH Range	0–14 (material/module-dependent)
Porosity	45 ± 5%

Material & Coating Combinations

Support Material	Available Coatings	Characteristics
Alumina (Al_2O_3)	Zirconia (ZrO_2)	Chemically and thermally stable, high mechanical strength
Silicon Carbide (SiC)	SiC	Superior corrosion and temperature resistance

Separation Layer Options

Membrane Type	Pore Size	Typical Applications
Microfiltration (MF)	200 *nm*	Clarification, bacteria/ colloid removal
Ultrafiltration (UF)	50, 100 *nm*	Virus removal, protein/enzyme separation

www.npceram.com
linkedin.com/company/nano-pa-layesh-ceram-npc/
Tel.: +98 21 88590873-Int.243
Fax: +98 21 88686168
Info@npceram.com
Office: 3rd Floor, No. 2, East 32nd Street, South Allameh Ave., Sa'adat Abad, Tehran, Postal Code: 1997816154, Iran.

Flat Sheet Ceramic Membrane

Model Code: NPC-F-200

Application

- **Food & Beverage:** Clarification, microbial control, protein recovery
- **Pharma & Biotech:** Cell broth filtration, enzyme separation
- **Petrochemical:** Oil-water separation, catalyst recovery
- **Water Treatment:** MBR polishing, RO pretreatment

Advantages

- High filtration area in a compact flat sheet design
- Designed for low-pressure or vacuum-driven filtration
- Excellent thermal and chemical resistance
- Suitable for dead-end, cross-flow, and submerged MBR configurations
- Easy to integrate into modular racks or custom housings
- Compatible with CIP and backflush protocols

Imp: Typical Pure Water Permeability: ~5,000 LMH/bar for 100 nm and ~6,000–7,000 LMH/bar for 200 nm (based on SiC flat sheet membranes under standard conditions: 25°C, vacuum operation)



www.npceram.com
linkedin.com/company/nano-palayesh-ceram-npc/
Tel.: +98 21 88590873-Int.243
Fax: +98 21 88686168
Info@npceram.com
Office: 3rd Floor, No. 2, East 32nd Street, South Allameh Ave., Sa'adat Abad, Tehran, Postal Code: 1997816154, Iran.